

ساب رود RP- 804 دهانات خاصة لتخطيط الطرق (مطاط مكلور)

الوصف:

- دهانات جاهزة من مركب واحد أساسها مطاط مكلور وأصباغ ومواد مالئة خاصة على شكل سائل أسود أو أبيض أو أصفر .

▪ المواصفة القياسية : Type F AASHTO Designation : M 248

مجالات الاستعمال:

- تخطيط الشوارع والطرق ومهابط الطائرات والجراجات والملاعب وعمل علامات المرور للأرضيات الإسفلتية والخرسانية .

المميزات:

- مقاومة عالية وثابتة للعوامل الجوية والمواد الكيماوية والزيوت والوقود .
- سهل الاستعمال.
- ثابت الألوان .

المواصفات الفنية:

- نسبة المواد الصلبة : 60%.
- الكثافة : 1.35 كجم / لتر
- زمن الجفاف (عند 25 درجة مئوية) : 5 دقيقة (سطحى)، 15 دقيقة (صلد)
- معدل الاستهلاك : 250 جم / م² / وجه
- سمك طبقة الدهان : 150 ميكرون

طريقة الاستعمال:

- تنظيف الأرضيات جيدا من الزيوت والشحوم و الأتربة
- تدهن طبقة واحدة أو أكثر طبقا للمواصفات المطلوبة وذلك باستعمال الفرشاة أو الرولة أو مسدس الرش او ماكينة التخطيط.

مدة التخزين :

- عامان من تاريخ الإنتاج .

العبوات :

- 25 كجم.

لمزيد من المعلومات برجاء الاتصال بخدمة الدعم الفني

SAP ROAD RP-804

Special Paints for Marking Roads

Description:

- Ready- to- apply paints, one compound, based on Chlorinated rubber, pigments and special filling materials on liquid form black , white & yellow.
- **Standard Specification :** **AASHTO Designation : M 248 Type F**

Fields of application:

- Marking Concrete and asphalt flooring of roads, highways, garages, parking areas and playgrounds.

Advantages :

- Constant & fast Resistant to chemicals, fuels, oil and water.
- Easy to use.
- Constant colors.

Technical data:

- **Solid content** : 60%
- **Specific gravity** : 1,35 kg / L
- **Tack free(at25°C)** : 5 minutes
- **Hard drying time (at 25 °C)** : 15 minutes
- **Colors** : black- white-yellow
- **Rate of use/coat** : 250gm/m²
- **Suggested D.F.T** : 150 micron

Directions for use:

- The surface to be coated should be free of dust, oil grease & loose particles.
- Apply one coat or more according to the required specifications by using brush, roller or sprayer.

Packages:

- 25 kg.

Storage life:

- Two years.

For more information please consult our technical department